





中国认可 国际互认 检测 TESTING CNAS L0599

Date:October 30,2020

Page 1 of 3

ELDO CARE CORPORATION LIMITED

RM.1902, EASEY COMM. BLDG., 253-261 HENNESSY ROAD, WANCHAI, HONGKONG

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)GIMA BRANDED 20686 - 3 PLY SURGICAL MASK - DISPOSABLE -

EARLOOP - FANTASY: PEACE

Composition : (A)67% non-woven, 33% melt-blown

Sample Color : (A)FANTASY: PEACE

Style No. : ELFM3600 Lot No. : Not provided

Manufacturer : ELDO CARE CO., LIMITED

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Oct 19, 2020

Testing Period : Oct 21, 2020 - Oct 30, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Signed for and on behalf of

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Helen Xuan (Authorized Signatory)





Test Report Test Result

SL52045300698601TX

Date:October 30,2020

Page 2 of 3

EN 14683:2019+AC:2019 Medical Face Masks-Requirements and Test Methods

Clause 5.2 Performance Requirement

Clause 5.2.2 Bacterial Filtration Efficiency (BFE)

(EN 14683:2019+AC:2019 Annex B)

Sample: A

Test Side Inside

Test Area Approximately 60 cm²

Flow Rate 28.3 L/min

Pre-Conditioning : Minimum of 4 hours at 21±5°C and 85±5% R.H.

: ~175mm x 165mm Dimensions of test specimen

Positive Control Average : 2450 CFU Negative Monitor Count : < 1 CFU Mean Particle Size : 3.0 ±0.3µm

Test bacteria : Staphylococcus aureus ATCC 6538

Test Item	Specimen No.	Result	
Bacterial Filtration Efficiency (BFE)	1	99.9%	
	2	99.9%	
	3	99.9%	
	4	99.9%	
	5	99.9%	

- 1) Performance Requirement: Type I≥95%, Type II≥98%, Type IIR ≥98%
- The number of specimens that shall be tested is minimum 5, but can be greater and shall be increased if necessary to allow for an AQL(Acceptable Quality Level) of 4%.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 t (86-21) 61402666 f (86-21) 64958763

中国・上海・徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666 f (86-21) 64958763 e sgs.china@sgs.com




SL52045300698601TX

Date:October 30,2020

Page 3 of 3





The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

End of Report







Date:October 30,2020



中国认可 国际互认 检测 TESTING CNAS L0599

Page 1 of 3

Test Report

SL52045300639501TX

ELDO CARE CORPORATION LIMITED

RM.1902, EASEY COMM. BLDG., 253-261 HENNESSY ROAD, WANCHAI, HONGKONG

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)GIMA BRANDED 20686 - 3 PLY SURGICAL MASK - DISPOSABLE -

EARLOOP - FANTASY: PEACE

Composition : (A)67% non-woven, 33% melt-blown

Sample Color : (A)FANTASY: PEACE

Style No. : ELFM3600 Lot No. : Not provided

Manufacturer : ELDO CARE CO., LIMITED

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Oct 19, 2020


Testing Period : Oct 20, 2020 - Oct 30, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Signed for and on behalf of

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center







SL52045300639501TX

Date:October 30,2020

Page 2 of 3

Test Result

EN 14683:2019+AC:2019 Medical Face Masks-Requirements and Test Methods

Clause 5.2 Performance Requirement

Clause 5.2.3 Breathability

(EN 14683 :2019+AC:2019 Annex C)

Sample: A

Test Side Randomly test in different location (1 around and 4 away from the centric

point) on each of the 5 masks

Pre-Conditioning Minimum of 4 hours at 21±5°C and 85±5% R.H.

Test Area 4.9 cm² Flow Rate 8 I/min

Specimen No.	Test Area No.	Different Pressure for each	The average value for each test	
		tested area (Pa/cm²)	specimen (Pa/cm²)	
	1-1	34.6		
	1-2	38.2		
1	1-3	39.3	38	
	1-4	39.2		
	1-5	39.4		
	2-1	38.8		
	2-2	38.5		
2	2-3	33.7	37	
	2-4	36.5		
	2-5	38.2		
3	3-1	39.6		
	3-2	38.9	38	
	3-3	34.6		
	3-4	36.2		
	3-5	38.9		
4	4-1	39.1		
	4-2	37.2		
	4-3	38.4	38	
	4-4	38.3		
	4-5	36.7		
5	5-1	39.4		
	5-2	38.5		
	5-3	39.0	39	
	5-4	37.3		
	5-5	38.9	7	

Remark:

- 1) Performance Requirement: Type I<40 Pa/cm², Type II<40 Pa/cm², Type IIR<60 Pa/cm²
- The number of specimens that shall be tested is minimum 5, but can be greater and shall be increased if necessary to allow for an AQL(Acceptable Quality Level) of 4%.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 t (86-21) 61402666 f (86-21) 64958763

中国・上海・徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666 f (86-21) 64958763 e sgs.china@sgs.com



SL52045300639501TX

Date:October 30,2020

Page 3 of 3





The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

End of Report











Date:October 30,2020

Page 1 of 3

ELDO CARE CORPORATION LIMITED

RM.1902, EASEY COMM. BLDG., 253-261 HENNESSY ROAD, WANCHAI, HONGKONG

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)GIMA BRANDED 20686 - 3 PLY SURGICAL MASK - DISPOSABLE -

EARLOOP - FANTASY: PEACE

Composition : (A)67% non-woven, 33% melt-blown

Sample Color : (A)FANTASY: PEACE

Style No. : ELFM3600 Lot No. : Not provided

Manufacturer : ELDO CARE CO., LIMITED

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Oct 19, 2020


Testing Period : Oct 20, 2020 - Oct 30, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Signed for and on behalf of

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center







Test Report Test Result SL52045300649801TX

Date:October 30,2020

Page 2 of 3

EN 14683:2019+AC:2019 Medical Face Masks-Requirements and Test Methods

Clause 5.2 Performance Requirement

Clause 5.2.4 Splash Resistance

(ISO 22609:2004)

Sample: A

Test Blood Pressure : 16.0kPa

Pre-Conditioning : Minimum of 4 hours at 21±5°C and 85±5% R.H.

Distance of the mask to the tip of cannula : 300±10mm

Test Specimen#	Penetration on inside surface	Conclusion	Test Specimen#	Penetration on inside surface	Conclusion
1	None Seen	Pass	17	None Seen	Pass
2	None Seen	Pass	18	None Seen	Pass
3	None Seen	Pass	19	None Seen	Pass
4	None Seen	Pass	20	None Seen	Pass
5	None Seen	Pass	21	None Seen	Pass
6	None Seen	Pass	22	None Seen	Pass
7	None Seen	Pass	23	None Seen	Pass
8	None Seen	Pass	24	None Seen	Pass
9	None Seen	Pass	25	None Seen	Pass
10	None Seen	Pass	26	None Seen	Pass
11	None Seen	Pass	27	None Seen	Pass
12	None Seen	Pass	28	None Seen	Pass
13	None Seen	Pass	29	None Seen	Pass
14	None Seen	Pass	30	None Seen	Pass
15	None Seen	Pass	31	None Seen	Pass
16	None Seen	Pass	32	None Seen	Pass
Number of Pass:		32			
Overal	Overall result: Acceptable				

Remark:

- 1) Performance Requirement Type I: N/A, Type II: N/A, Type IIR: ≥16.0kPa
- 2) Test was conducted within 60s after removal from conditioning chamber.
- 3) An acceptable quality limit of 4.0% is met for a single sampling plan when 29 or more of the 32 tested specimens show pass results.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3¹¹Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮編: 200233 t (86-21) 61402666 t (86-21) 61402666

f (86-21) 64958763 f (86-21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com




SL52045300649801TX

Date:October 30,2020

Page 3 of 3





The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

www.sgsgroup.com.cn







中国认可 国际互认 检测 TESTING CNAS L0599

Date:November 20,2020

Page 1 of 3

ELDO CARE CORPORATION LIMITED

RM.1902, EASEY COMM. BLDG., 253-261 HENNESSY ROAD, WANCHAI, HONGKONG

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)GIMA BRANDED 20686 - 3 PLY SURGICAL MASK - DISPOSABLE-

EARLOOP - FANTASY: PEACE

Composition : (A)67% non-woven, 33% melt-blown

Sample Color : (A)FANTASY: PEACE

Style No. : ELFM3600 Lot No. : Not provided

Manufacturer : ELDO CARE CO., LIMITED

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Nov 10, 2020

Testing Period : Nov 11, 2020 - Nov 20, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Signed for and on behalf of

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Sara Guo (Account Executive)

Dongjing Liu (Authorized Signatory)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's esponsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or, email: CN.Doccheck@sgs.com



SL52045312279201TX

Date:November 20,2020

Page 2 of 3

Test Result

EN 14683:2019+AC:2019 Medical Face Masks-Requirements and Test Methods

Clause 5.2 Performance Requirement

Clause 5.2.5 Microbial Cleanliness

(EN 14683:2019+AC:2019 Annex D and EN ISO 11737-1:2018)

Sample: A

Test Specimen#	Mask Weight(g)	Total Bioburden, (CFU/mask)	Total Bioburden, (CFU/g)
1#	3.61	12	3.32
2#	3.62	15	4.14
3#	3.64	9	2.47
4#	3.58	12	3.35
5#	3.62	6	1.66

Remark: Performance Requirement: Type I≤30 CFU/g, Type II≤30 CFU/g, Type IIR≤30 CFU/g





SL52045312279201TX

Date:November 20,2020

Page 3 of 3





The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

End of Report

